

Lithium Moly Grease

Multipurpose Lithium Grease with Moly

Brautek Lithium Moly 1 es grasa base de litio. Se fabrica con arena de aceite base de calidad superior fortificada con una combinación sinérgica de Moly. Se mejora con otros aditivos de rendimiento que cumplen y/o exceden los requisitos severos del equipo.

Grasa Moly de litio contiene disulfuro de molibdeno. Esta grasa no se va a eliminar, sino que formará una película adherente en superficies metálicas, al tiempo que reduce el coeficiente de fricción. Este producto se puede utilizar en una serie de aplicaciones y tiene un rango de temperatura de funcionamiento de pie. La combinación de disulfuro de molibdeno actuará como lubricante seco cuando sea necesario. Esta grasa también está disponible en grado NLGI#1.

Product Features:

- Lithium base makes for high temperature capabilities
- Excellent thermal and oxidation stability
- Outstanding load carrying properties
- Tacky and better film formation on lubrication area
- Capable of effective lubrication under boundary lubrication conditions

Customer Benefits:

- Superior lubrication under extreme conditions
- Stays in place in extreme environment to protect your components
- Will withstand severe shocks and vibrations
- Rust inhibitors help protect equipment
- Excellent water washout characteristics

Applications:

- Automotive, industrial, fleet trucks and contractor service.
- The characteristics are especially valuable in heavy-duty applications where sliding or oscillating motion is present as in bearings, steering linkage and fifth wheel assemblies.
- Robust multi-purpose grease for a wide range of applications.

Typical Properties

LITHIUM MOLY GREASE

Product Number	903MA	903MB	Test Method
Color	Gray-Black	Gray-Black	Visual
Texture	Smooth, Tacky	Smooth, Tacky	Visual
Thickener Type	Lithium	Lithium	-
NLGI Grade	2	1	ASTM D 217
Worked Penetration @ 25°C	285	320	ASTM D 217
Drop Point, °C	200 min	200 Min	ASTM D 2265
Viscosity @ 40°C, cSt	220	220	ASTM D 445
Viscosity @ 100°C, cSt	19.5	19.5	ASTM D 445
Viscosity @ 100°F, SUS	1185	1185	ASTM D 445
Viscosity @ 210°F, SUS	95	95	ASTM D 445
4-Ball EP Load, kg	400	400	ASTM D 2596
Load Wear Index	65	65	ASTM D 2596
Timken OK load, lbs	60	60	ASTM D 2509
Wheel Bearing Leakage, gm, max.	5 max	5	ASTM D 4290

These properties are typical of the current production. Variations that do not affect product performance are to be expected depending on blending and manufacturing locations. The information above is subject to change without notice.

Health and Safety:

This product is unlikely to have any adverse health implications or safety hazards when used for its intended application. Avoid contact with skin, use resistant gloves when handling used oil. If skin comes in contact wash immediately with soap and water. For complete information on safe handling and product characteristics please refer to the Material Safety Data Sheet (MSDS) found on our website. www.brautek.com